

 heating the support and the photosensitive coated layer by a second heating means provided at a downstream side of the first heating means so that hardening of the photosensitive coated layer is promoted; and
changing a condition of heating of the second heating means while the support is being conveyed.

 2. (Amended) A method for manufacturing a lithographic printing plate according to claim 1, wherein the first heating means heats the photosensitive coated layer to 90°C or more.

3. (Amended) A method for manufacturing a lithographic printing plate according to claim 1, wherein the first heating means dries the photosensitive coated layer such that a remaining amount of the organic solvent in the photosensitive coated layer is 5 wt% or less of the photosensitive coated layer.

 9. (Amended) A method for manufacturing a lithographic printing plate according to claim 1, wherein the condition of heating by the second heating means is controlled in accordance with a type of the photosensitive coated layer formed on the support, such that a temperature of the photosensitive coated layer immediately after heating by the second heating means is a predetermined temperature which is set in accordance with the type of the photosensitive coated layer.

12. (Amended) A method for manufacturing a lithographic printing plate, the method comprising:

supplying a plurality of supports that have different dimensions, each of the supports being coated with a photosensitive coating solution containing an organic solvent such that a photosensitive coated layer is formed by the photosensitive coating solution;

drying the photosensitive coated layer by a first heating means to a dry-to-touch state;

heating the support and the photosensitive coated layer by a second heating means provided at a downstream side of the first heating means so that hardening of the photosensitive coated layer is promoted;

changing a condition of heating the supports and photosensitive coated layers by the second heating means in accordance with the thicknesses and the widths of the supports.

17. (Amended) A method for manufacturing a lithographic printing plate according to claim 1, further comprising, at a down stream side of the cooling step, a step of forming an overcoat layer on the photosensitive coated layer.

Please add the following new claims:

18. (New) A method for manufacturing a lithographic printing plate according to claim 12, wherein the first heating means heats the photosensitive coated layer to 90°C or more.

AMENDMENT UNDER 37 C.F.R. § 1.111
U.S. Appl. No. 09/895,264 (Q64664)

19. (New) A method for manufacturing a lithographic printing plate according to claim 12, wherein the first heating means dries the photosensitive coated layer such that a remaining amount of the organic solvent in the photosensitive coated layer is 5 wt% or less of the photosensitive coated layer.

20. (New) A method for manufacturing a lithographic printing plate according to claim 12, wherein a heating system of the second heating means is a heat radiation system.

21. (New) A method for manufacturing a lithographic printing plate according to claim 12, wherein a heating system of the second heating means is an induction heating system.

22. (New) A method for manufacturing a lithographic printing plate according to claim 12, wherein the condition of heating by the second heating means is controlled in accordance with a type of the photosensitive coated layer formed on the support, such that a temperature of the photosensitive coated layer immediately after heating by the second heating means is a predetermined temperature which is set in accordance with the type of the photosensitive coated layer.

23. (New) A method for manufacturing a lithographic printing plate according to claim 1, wherein the second heating means is a plurality of drying devices which are disposed

along a conveying path of the support, and amounts of heat supplied by the plurality of heating devices are respectively controlled in accordance with changes in dimensions of the supports.

Sub
AS
amend
24. (New) A method for manufacturing a lithographic printing plate according to claim 12, wherein after hot air drying of the coated layer by the first heating means, the second heating means radiates mid-infrared radiation or far infrared radiation to the photosensitive coated layer and the support so as to heat the support and the photosensitive coated layer.

25. (New) A method for manufacturing a lithographic printing plate according to claim 12, further comprising, at a down stream side of the cooling step, a step of forming an overcoat layer on the photosensitive coated layer.
